



Flexboard

DO

- Attach to framework before applying decorative surfacing material. Should be installed using conventional fabrication methods.
- Attach to framework using glues, staples or nails.
- Always attach to horizontal support ribs. The use of three ribs (top, middle, & bottom) is recommended.
- Use of Vertical Grade HPL as a decorative surfacing material is preferred. A Horizontal Grade HPL can be used, provided it will bend to the desired radius.
- Any type of face veneer can be used as the decorative surfacing material. (10 mil paperback, wood on wood two-ply, phenolic-backed veneer, etc.)
- Flexboard can be laminated flat using a single-ply veneer and then bending down to a 16” radius.

DON'T

- **DO NOT** laminate flat when using HPL, Phenolic-Backed veneer or other stiff materials.
- **DO NOT** attach to vertical ribs except where seaming is to be done. If vertical ribs are used, attaching through these ribs may deflect the panel and distort the shape.
- **DO NOT** attach product directly onto drywall.
- **AVOID** allowing decorative surfacing material to end on a radius. Especially horizontal grade laminates or other similarly rigid materials.

For additional fabrication tips please visit the Fabrication Steps or Technical Guide sections at www.kerfkore.com. For application questions and technical assistance, call us at 800-637-3539.

Components are CARB II and TSCA Title VI compliant Third Party Certified



912 264 6496



kerfkore.com



2630 Sidney Lanier Drive Brunswick, GA 31525